

# Comparative study on Normal Concrete & Bendable Concrete

Prof. Shital H. Ingle<sup>1</sup>, Miss. Snehal C. Galwade<sup>2</sup>, Mr. Premsing C. Solanke<sup>3</sup>,

Mr. Ritesh Y. Sonar<sup>4</sup>, Miss. Prachi S. Koli<sup>5</sup>,

<sup>1</sup>Lecturer of Department, Civil Engineering Department, Padm. Dr. V. B. Kolte college of Engg.  
Maharashtra, India

<sup>2,3,4,5</sup>Student of Civil Engineering, Padm. Dr. V. B. Kolte College of Engineering, Malkapur, Maharashtra,  
India

DOI: 10.5281/zenodo.19248581

## ABSTRACT

*Concrete is the most widely used construction material in the world due to its high compressive strength, availability of raw materials, and versatility in structural applications. However, conventional concrete exhibits inherently brittle behavior with low tensile strength and limited strain capacity, which often leads to cracking, durability issues, and premature structural failure. To overcome these limitations, an innovative material known as bendable concrete or Engineered Cementitious Composite (ECC) has been developed. Bendable concrete is characterized by high ductility, strain-hardening behavior, and the ability to undergo significant deformation without sudden failure. This research presents a comprehensive comparative study between bendable concrete and normal concrete, focusing on their material composition, mechanical properties, flexural behavior, crack control mechanisms, durability, sustainability, and practical applications. The methodology adopted in this study is primarily based on an extensive review of published research papers, experimental studies, and recent advancements in ECC technology. Key performance parameters such as compressive strength, tensile strength, flexural strength, ductility, crack width, and durability under environmental exposure are critically analyzed. The comparison reveals that while normal concrete performs adequately under compressive loads, it exhibits brittle failure under tensile stress. In contrast, bendable concrete demonstrates superior tensile strain capacity, controlled micro-cracking, and enhanced durability, making it particularly suitable for seismic-resistant structures, pavements, and repair works. The study concludes that although bendable concrete involves higher initial material costs, its long-term benefits in terms of service life, reduced maintenance, and structural resilience justify its adoption in modern infrastructure development.*

## 1. INTRODUCTION

Concrete has been an indispensable material in the construction industry for centuries, forming the backbone of modern infrastructure such as buildings, bridges, pavements, dams, and tunnels. Its popularity stems from its excellent compressive strength, moldability, fire resistance, and relatively low cost. Despite these advantages, conventional concrete suffers from several inherent drawbacks, the most significant being its low tensile strength and brittle nature. Under tensile or flexural loading, normal concrete tends to crack easily and fails abruptly without sufficient warning, which compromises structural safety and durability.

Cracking in concrete structures is a critical issue that affects both serviceability and durability. Cracks allow the ingress of water, chlorides, and other aggressive agents, leading to corrosion of reinforcement, loss of cross-sectional area, and eventual structural deterioration. To mitigate this problem, steel reinforcement is commonly used to carry tensile stresses. While reinforced concrete improves structural performance, cracking cannot be completely eliminated, and maintenance costs remain high over the structure's lifespan. In recent decades, significant research has been directed toward developing advanced cementitious materials with improved tensile behavior and ductility. One of the most promising developments in this field is bendable concrete, technically known as Engineered Cementitious Composite (ECC). Unlike conventional fiber-reinforced concrete, ECC is designed based on micromechanical principles to achieve strain-hardening behavior under tensile loading. This enables the material to sustain multiple micro-cracks with tightly controlled crack widths rather than forming a few large cracks.

Bendable concrete typically incorporates fine aggregates, a high cementitious content, supplementary cementitious materials such as fly ash, and a small volume fraction of high-performance fibers, commonly polyvinyl alcohol (PVA) fibers. These fibers play a crucial role in bridging cracks and distributing stresses

uniformly across the material. As a result, ECC exhibits tensile strain capacities several hundred times greater than that of normal concrete, along with exceptional energy absorption capacity. The growing demand for resilient infrastructure capable of withstanding extreme loading conditions such as earthquakes, heavy traffic, and environmental degradation has increased interest in bendable concrete. Its superior crack control and durability make it particularly suitable for applications such as bridge decks, pavement overlays, seismic dampers, and repair and rehabilitation works. However, despite its advantages, bendable concrete is not yet widely adopted due to factors such as higher material costs, lack of standardized design codes, and limited awareness among practicing engineers.

This research aims to provide a detailed comparative study between normal concrete and bendable concrete by examining their fundamental properties, performance characteristics, and practical implications. By critically analyzing existing literature and experimental findings, this study seeks to highlight the potential of bendable concrete as a viable alternative to conventional concrete in future construction practices.

## 2. OBJECTIVES OF THE STUDY

The main objectives of this research paper are:

- To study the fundamental properties and behaviour of normal concrete.
- To understand the concept, composition, and working mechanism of bendable concrete (ECC).
- To compare the mechanical properties of normal concrete and bendable concrete.
- To evaluate crack behaviour, ductility, and durability characteristics of both materials.
- To review recent research and developments in bendable concrete technology.
- To assess the advantages, limitations, and practical applications of bendable concrete.

## 3. METHODOLOGY

The methodology adopted for this comparative study is primarily based on an extensive review of existing literature, research papers, technical journals, conference proceedings, and experimental studies related to bendable concrete and normal concrete. The study follows a qualitative and analytical approach, focusing on understanding material behaviour rather than conducting laboratory experiments.

The methodology includes the following steps:

1. Collection of data from published research papers on normal concrete and bendable concrete.
2. Study of material composition, mix design principles, and mechanical properties.
3. Comparative analysis of tensile strength, compressive strength, flexural strength, ductility, and crack control behaviour.
4. Review of durability aspects such as resistance to corrosion, shrinkage cracking, fatigue, and environmental exposure.
5. Examination of recent innovations and sustainable approaches in bendable concrete.
6. Compilation and interpretation of findings to draw meaningful conclusions.

## 4. OVERVIEW OF NORMAL CONCRETE

### Definition

Normal concrete is a composite material composed of cement, fine aggregates (sand), coarse aggregates (gravel or crushed stone), and water. It may also include admixtures to improve workability, setting time, and strength. Normal concrete is designed primarily to resist compressive stresses and is widely used in buildings, bridges, pavements, dams, and other infrastructure projects.

### Properties of Normal Concrete

- High compressive strength: Typically, 20–40 MPa at 28 days.
- Low tensile strength: About 8–12% of compressive strength.
- Brittle behaviour: Low ductility and strain capacity.
- Durability: Good when properly mixed, placed, and cured.
- Fire resistance: Offers good protection against fire.
- Workability: Depends on water–cement ratio and aggregate quality.
- Permeability: Higher crack widths increase permeability, reducing durability.
- Economical and readily available material.

### Failure Behavior of Normal Concrete

- Brittle failure: Sudden cracking and loss of load-carrying capacity under tensile stress.
- Elastic behaviour: Up to a certain stress level before cracking.
- Cracking: Initiates as microcracks due to shrinkage or thermal stresses; propagates rapidly under load.

- Compression failure: Crushing accompanied by diagonal cracks.
- Tension/flexure failure: Sudden and brittle with wide crack formation.
- Durability impact: Cracks allow ingress of water and chemicals, accelerating reinforcement corrosion and shortening service life.

## 5. OVERVIEW OF BENDABLE CONCRETE (ECC)

### Definition

Bendable concrete, also known as Engineered Cementitious Composite (ECC), is a high-performance Fiber-reinforced cementitious material that exhibits exceptional ductility and strain-hardening behaviour. It is designed using micromechanical principles to control crack formation and propagation.

### Composition of Bendable Concrete

The typical composition of bendable concrete includes:

- Ordinary Portland Cement
- Fine aggregates (usually silica sand)
- Fly ash or supplementary cementitious materials
- Water
- Chemical admixtures
- Microfibers (such as Polyvinyl Alcohol (PVA), polyethylene, or steel Fibers)

Unlike normal concrete, ECC does not use coarse aggregates. The absence of coarse aggregates helps in achieving uniform Fiber distribution and enhanced ductility.

### Mechanism of Bendability

The bendability of ECC is achieved through the interaction between fibers and the cement matrix. When tensile stress is applied, multiple micro-cracks form instead of a single large crack. The fibers bridge these cracks, preventing sudden failure and allowing the material to undergo large deformation while sustaining load.

## 6. COMPARISON BETWEEN NORMAL CONCRETE & BENDABLE CONCRETE

| Point                 | Normal Concrete                                                 | Bendable Concrete (ECC)                         |
|-----------------------|-----------------------------------------------------------------|-------------------------------------------------|
| Definition            | Traditional concrete made of cement, sand, aggregate, and water | Special concrete that can bend without cracking |
| Flexibility           | Very low (brittle in nature)                                    | Very high (can bend up to 3–5%)                 |
| Crack Behavior        | Forms wide cracks suddenly                                      | Forms many very fine micro-cracks               |
| Tensile Strength      | Low                                                             | High                                            |
| Compressive Strength  | High                                                            | Comparable or slightly lower                    |
| Ductility             | Very low                                                        | Very high                                       |
| Use of Aggregate      | Coarse aggregate used                                           | No coarse aggregate (only fine sand)            |
| Reinforcement Need    | Steel reinforcement required                                    | Requires less steel reinforcement               |
| Durability            | Moderate                                                        | Very high (self-healing cracks)                 |
| Earthquake Resistance | Poor                                                            | Excellent                                       |
| Maintenance           | High                                                            | Low                                             |
| Cost                  | Low                                                             | High                                            |
| Life Span             | Normal                                                          | Longer than normal concrete                     |

## 7. LIMITATIONS OF BENDABLE CONCRETE

- **High initial cost**  
Bendable concrete is more expensive than normal concrete due to the use of special fibers (PVA, PE) and admixtures.
- **Limited availability of materials**  
Required fibers and ingredients are not easily available in all regions, especially in developing areas.
- **Complex mix design**  
The mix proportion is sensitive and needs precise control during batching and mixing.
- **Skilled workmanship required**  
Proper mixing, placing, and curing need trained labor and technical supervision.
- **Lower compressive strength than high-grade concrete**

Although ductility is high, compressive strength may be lower compared to high-strength conventional concrete.

- **Lack of standard design codes**

Design guidelines and codes are still limited compared to conventional RCC.


- **Not suitable for all structures**

Due to cost and complexity, it is generally used only in special structures like bridges, seismic zones, and repair works.

- **Quality control issues**

Small errors in mixing or fiber distribution can significantly affect performance.

## 8. STRESS–STRAIN BEHAVIOR OF NORMAL CONCRETE AND ENGINEERED CEMENTITIOUS COMPOSITE (ECC)



## 9. ADVANTAGES OF BENDABLE CONCRETE

1. **High ductility (flexibility)**

- Can bend and deform without sudden cracking or failure
- Strain capacity is 100–500 times greater than normal concrete

2. **Crack control**

- Forms many tiny, hairline cracks instead of large visible cracks
- Crack widths typically stay under 0.1 mm, which improves longevity

3. **Improved durability**

- Small cracks limit water and chemical penetration
- Better resistance to corrosion, freeze–thaw cycles, and chemical attack

4. **Earthquake resistance**

- Absorbs and dissipates energy during seismic events
- Reduces structural damage and risk of collapse

5. **Higher tensile strength**

- Performs well under tension without needing heavy steel reinforcement
- Ideal for thin or lightweight structural elements

6. **Self-healing capability**

- Microcracks can close over time through hydration and mineral precipitation
- Extends service life with less maintenance

7. **Reduced maintenance costs**

- Fewer repairs due to controlled cracking and durability
- Lower life-cycle cost despite higher initial material cost

8. **Better impact and fatigue resistance**

- Suitable for bridges, pavements, and industrial floors exposed to repeated loading

9. **Design flexibility**

- Enables slimmer sections, curved forms, and innovative architectural designs

## 10. CONCLUSION

Bendable concrete, commonly referred to as Engineered Cementitious Composite (ECC), represents a significant advancement over conventional concrete by addressing its inherent brittleness and low tensile

capacity. Through the incorporation of high-performance fibers and optimized mix design, bendable concrete exhibits strain-hardening behavior, multiple micro-cracking, and superior ductility compared to normal concrete. These characteristics result in enhanced tensile strength, improved energy absorption, and exceptional crack control, which collectively contribute to increased durability and service life of structures.

The research clearly indicates that bendable concrete offers remarkable resistance to cracking, corrosion, fatigue, and seismic forces, making it highly suitable for applications in earthquake-resistant structures, bridge decks, pavements, retrofitting works, and thin structural elements. Although the initial material cost of bendable concrete is higher than that of conventional concrete, its long-term economic benefits—such as reduced maintenance, lower repair costs, and extended structural lifespan—justify its use in critical and high-performance infrastructure.

From a sustainability perspective, bendable concrete demonstrates potential for reduced environmental impact due to lower repair frequency and the possible use of industrial by-products such as fly ash. Despite certain limitations related to cost, fiber availability, and skilled workmanship requirements, ongoing research and technological advancements are expected to overcome these challenges.

In conclusion, bendable concrete is a promising construction material that combines strength, ductility, durability, and sustainability. Its adoption in modern infrastructure can significantly enhance structural performance and resilience, indicating a strong potential for widespread application in future civil engineering practices.

## 11. REFERENCE

- [1] Li, V. C., “Engineered Cementitious Composites (ECC) – Material, Structural, and Durability Performance,” Concrete Construction Engineering Handbook, CRC Press, 2008.
- [2] Li, V. C., Wang, S., and Wu, C., “Tensile Strain-Hardening Behavior of Polyvinyl Alcohol Engineered Cementitious Composites,” ACI Materials Journal, Vol. 98, No. 6, 2001, pp. 483–492.
- [3] Fischer, G., and Li, V. C., “Effect of Fiber Reinforcement on the Response of Structural Members,” Engineering Structures, Vol. 25, No. 6, 2003, pp. 711–722.
- [4] Sahmaran, M., and Li, V. C., “Durability Properties of Micro-Cracked ECC Containing High Volumes of Fly Ash,” Cement and Concrete Research, Vol. 39, 2009, pp. 1033–1043.
- [5] Wang, S., and Li, V. C., “Engineered Cementitious Composites with High-Volume Fly Ash,” ACI Materials Journal, Vol. 104, No. 3, 2007, pp. 233–241.
- [6] Mehta, P. K., and Monteiro, P. J. M., Concrete: Microstructure, Properties, and Materials, 4th Edition, McGraw- Hill Education, 2014.
- [7] Neville, A. M., Properties of Concrete, 5th Edition, Pearson Education, 2011.
- [8] Naaman, A. E., “High Performance Fiber Reinforced Cement Composites,” ACI Materials Journal, Vol. 94, No. 4, 1997, pp. 336–347.
- [9] Kallepalli, B. M., Reddy, V. S., and Kumar, P. R., “Experimental Study on Bendable Concrete,” International Journal of Engineering Research & Technology (IJERT), Vol. 6, Issue 4, 2017.
- [10] Khitab, A., “Flexible Engineered Cementitious Composites,” The Constructor – Civil Engineering Home, 2019.
- [11] Yang, E. H., Wang, S., Yang, Y., and Li, V. C., “Fiber Bridging Constitutive Law of Engineered Cementitious Composites,” Journal of Advanced Concrete Technology, Vol. 6, No. 1, 2008, pp. 181–193.
- [12] ASTM C39 / C39M-23, “Standard Test Method for Compressive Strength of Cylindrical Concrete Specimens,” ASTM International.
- [13] IS 456:2000, Plain and Reinforced Concrete – Code of Practice, Bureau of Indian Standards, New Delhi.
- [14] IS 516:2021, Methods of Tests for Strength of Concrete, Bureau of Indian Standards, New Delhi.
- [15] Victor, D. J., and Kumaran, S. S., “Flexural Behavior of Engineered Cementitious Composite Beams,” Construction and Building Materials, Vol. 30, 2012, pp. 1–7.
- [16] Engineered Cementitious Composites,” ACI Materials Journal, Vol. 98, No. 6, 2001, pp. 483–492.