

Detailed Analysis of Pervious Concrete

Prof. Shital H. Ingle¹, Miss. Nikita D. Bhojane², Mr. Sanket G. Patil³,
Mr. Vivek S. Fardale⁴, Mr. Gaurav N. Koli⁵,

¹Lecturer of Department, Civil Engineering Department, Padm. Dr. V. B. Kolte college of Engg.

Maharashtra, India

^{2,3,4,5}Student of Civil Engineering, Padm. Dr. V. B. Kolte College of Engineering, Malkapur, Maharashtra, India

DOI: 10.5281/zenodo.19248775

ABSTRACT

Concrete has been the most widely used construction material for more than a century due to its versatility, strength, and durability. However, a large number of existing structures today are made using older concrete technologies, materials, and construction practices. The detailed analysis of previous (aged) concrete is essential for assessing structural safety, planning rehabilitation, and extending the service life of existing infrastructure. This paper presents a comprehensive analysis of previous concrete, focusing on its material properties, degradation mechanisms, mechanical performance, and durability characteristics. The study is based on a critical review of past research findings, standard testing practices, and observed field performance of old concrete structures. The paper highlights the differences between earlier concrete and modern concrete, identifies key factors responsible for deterioration, and discusses the engineering significance of evaluating previous concrete for repair and retrofitting purposes.

Keywords:- Previous concrete, aged concrete, durability, degradation, mechanical properties, structural assessment

1. INTRODUCTION

This research aims to provide a detailed comparative study between normal concrete and bendable concrete by examining their fundamental properties, performance characteristics, and practical implications. By critically analyzing existing literature and experimental findings, this study seeks to highlight the potential of bendable concrete as a viable alternative to conventional concrete in future construction practices. Concrete has played a vital role in the development of civil engineering infrastructure, including buildings, bridges, dams, and pavements. Many of these structures have been in service for several decades and are now classified as existing or previous concrete structures. With increasing age, concrete undergoes physical, chemical, and mechanical changes that may affect its performance and safety. The evaluation of previous concrete is therefore a critical task for engineers, especially in the context of sustainability, resource conservation, and infrastructure maintenance.

Earlier concrete was often designed with limited knowledge of durability, exposure conditions, and long-term behavior. Factors such as low cement quality, improper mix proportions, inadequate curing, and lack of durability considerations have contributed to the deterioration of many old concrete structures. This paper aims to provide a detailed analysis of previous concrete by examining its properties, common degradation mechanisms, and overall performance, based on existing research and practical observations.

2. OBJECTIVES OF THE STUDY

The main objectives of this research paper are:

- **To study the fundamental properties of pervious concrete**, including its structure, composition, and working mechanism.
- **To evaluate the permeability and drainage characteristics** of pervious concrete and its effectiveness in reducing surface runoff.
- **To investigate the mechanical properties** of pervious concrete, such as compressive strength, flexural strength, and durability.
- **To analyze the effect of different mix proportions**, aggregate sizes, and water–cement ratios on the performance of pervious concrete.
- **To compare pervious concrete with conventional concrete** in terms of strength, environmental impact, and functional performance.
- **To assess the role of pervious concrete in sustainable construction**, particularly in groundwater recharge and urban stormwater management.
- **To identify the limitations and challenges** associated with the use of pervious concrete in practical applications.

3. MATERIAL PROPERTIES OF PREVIOUS CONCRETE

Mechanical Properties

The compressive strength of previous concrete generally depends on the quality of materials used, mix proportioning, and curing practices. Studies have shown that old concrete may exhibit lower or highly variable compressive strength compared to modern concrete. Tensile and flexural strengths are often significantly reduced due to microcracking and long-term loading effects.

The modulus of elasticity of aged concrete may also decrease over time, especially in structures exposed to aggressive environments. This reduction affects stiffness and load distribution within structural members.

Physical Properties

Physical properties such as density, porosity, and permeability play a crucial role in the durability of previous concrete. Older concrete often has higher porosity due to poor compaction and higher water–cement ratios. Increased permeability allows harmful agents such as chlorides, sulfates, and carbon dioxide to penetrate the concrete, accelerating deterioration.

4. DEGRADATION MECHANISMS IN PREVIOUS CONCRETE

Carbonation

Carbonation is one of the most common degradation processes in old concrete structures. It occurs when carbon dioxide from the atmosphere reacts with calcium hydroxide in concrete, reducing the alkalinity. This process leads to corrosion of reinforcing steel once the protective alkaline environment is lost.

Chloride-Induced Corrosion

In coastal areas or regions where de-icing salts are used, chloride penetration is a major cause of reinforcement corrosion. Previous concrete, due to its higher permeability and insufficient cover, is particularly vulnerable to chloride attack.

Sulfate Attack

Sulfate attack results from the reaction between sulfate ions and cement hydration products, causing expansion, cracking, and loss of strength. Older concrete made with sulfate-susceptible cement is more prone to this form of deterioration.

Freeze–Thaw Damage

In cold regions, repeated freeze–thaw cycles can cause scaling, cracking, and surface deterioration in concrete. Earlier concrete often lacked air-entrainment, making it more susceptible to freeze–thaw damage.

5. MICROSTRUCTURAL CHANGES IN AGED CONCRETE

Microstructural analysis of previous concrete using techniques such as scanning electron microscopy (SEM) and X-ray diffraction (XRD) reveals significant changes over time. These include the formation of microcracks, leaching of calcium compounds, and alteration of hydration products. Such changes directly influence strength, durability, and overall performance.

6. METHODOLOGY

Material Selection

- **Cement:** Ordinary Portland Cement (OPC)
- **Coarse Aggregate:** Clean, single-sized aggregate (generally 10–20 mm)
- **Fine Aggregate:** Usually *not used* or used in very small quantity
- **Water:** Clean potable water
- **Admixtures (optional):** Superplasticizers or viscosity modifiers (if required)

Mix Proportioning

- Previous concrete is designed with **high void content (15–30%)**
- Typical mix ratios (by weight):
 - Cement : Coarse Aggregate = **1 : 4 to 1 : 6**
- **Water–cement ratio:** Low (generally **0.27–0.35**) to maintain paste coating without clogging pores

Mixing Process

- Coarse aggregates are first placed in the mixer
- Cement is added and mixed dry
- Water is added gradually

- Mixing continues until aggregates are uniformly coated with cement paste

7. OVERVIEW OF NORMAL CONCRETE

Definition

Normal concrete is a composite material composed of cement, fine aggregates (sand), coarse aggregates (gravel or crushed stone), and water. It may also include admixtures to improve workability, setting time, and strength. Normal concrete is designed primarily to resist compressive stresses and is widely used in buildings, bridges, pavements, dams, and other infrastructure projects.

Properties of Normal Concrete

- High compressive strength: Typically, 20–40 MPa at 28 days.
- Low tensile strength: About 8–12% of compressive strength.
- Brittle behaviour: Low ductility and strain capacity.
- Durability: Good when properly mixed, placed, and cured.
- Fire resistance: Offers good protection against fire.
- Workability: Depends on water–cement ratio and aggregate quality.
- Permeability: Higher crack widths increase permeability, reducing durability.
- Economical and readily available material.

Failure Behavior of Normal Concrete

- Brittle failure: Sudden cracking and loss of load-carrying capacity under tensile stress.
- Elastic behaviour: Up to a certain stress level before cracking.
- Cracking: Initiates as microcracks due to shrinkage or thermal stresses; propagates rapidly under load.
- Compression failure: Crushing accompanied by diagonal cracks.
- Tension/flexure failure: Sudden and brittle with wide crack formation.
- Durability impact: Cracks allow ingress of water and chemicals, accelerating reinforcement corrosion and shortening service life.

8. OVERVIEW OF PERVIOUS CONCRETE

Definition

Pervious concrete is a special type of concrete with a high level of interconnected voids that allow water to pass through it easily. Unlike conventional concrete, it contains little or no fine aggregate, which creates a porous structure. This makes pervious concrete an effective material for managing stormwater runoff and improving groundwater recharge.

Pervious concrete typically consists of cement, coarse aggregate, water, and sometimes admixtures. The void content generally ranges from 15% to 30%, enabling rapid infiltration of rainwater through the pavement surface into the underlying soil.

Composition of pervious Concrete

Pervious concrete is composed of a limited number of carefully selected materials to create a porous structure that allows water to pass through.

Cement

- Ordinary Portland Cement (OPC) is commonly used
- Acts as the binding material that coats the aggregates

Coarse Aggregate

- Single-sized, clean, angular aggregates (usually 10–20 mm)
- Main component of pervious concrete
- Creates interconnected voids for water permeability

Fine Aggregate

- Generally **not used** or used in very small quantity
- Absence of sand helps maintain porosity

Water

- Clean potable water
- Low water–cement ratio (0.27–0.35)
- Just enough to coat aggregates without filling pores

Admixtures (Optional)

- Superplasticizers to improve workability
- Viscosity-modifying agents to prevent paste drain-down
- Air-entraining agents (sometimes used)

Typical Proportions

- Cement : Coarse Aggregate = **1 : 4 to 1 : 6**
- Void content = **15–30%**

Mechanism of pervious concrete

The mechanism of pervious concrete is based on its ability to allow water to pass through its interconnected pore structure while still providing adequate structural support for light to moderate loads.

9. LIMITATIONS OF PERVIOUS CONCRETE

- **Low Compressive Strength**
Strength is lower than conventional concrete due to high void content.
- **Not Suitable for Heavy Loads**
Cannot be used for highways, heavy traffic roads, or industrial pavements.
- **Clogging of Pores**
Pores may become blocked by dust, silt, or debris, reducing permeability.
- **Careful Construction Required**
Requires precise mix design, placement, and compaction.
Over-compaction can close pores.
- **Higher Initial Cost**
Material and skilled labor costs can be higher compared to normal concrete.
- **Freeze–Thaw Issues**
Performance may reduce in regions with severe freeze–thaw cycles if not properly designed.
- **Limited Finishing Options**
Surface finishing is restricted because finishing can block voids.
- **Maintenance Requirement**
Periodic cleaning (vacuuming or pressure washing) is needed to maintain permeability.

10. CONCLUSION

Pervious concrete is an effective and sustainable construction material that plays a significant role in stormwater management and environmental protection. Its unique porous structure allows rainwater to infiltrate through the pavement, reducing surface runoff, minimizing flooding, and promoting groundwater recharge.

Although pervious concrete has lower compressive strength compared to conventional concrete, it provides sufficient performance for low-traffic applications such as parking lots, sidewalks, walkways, and pavements in parks. The studies reviewed indicate that its strength and permeability depend largely on proper mix design, aggregate grading, controlled compaction, and curing methods.

Despite challenges such as pore clogging, higher initial cost, and limited heavy-load applications, these limitations can be minimized through appropriate design, skilled construction practices, and regular maintenance. The use of supplementary cementitious materials further enhances durability and sustainability.

In conclusion, pervious concrete is a viable green alternative to conventional pavement materials and is particularly suitable for urban areas facing drainage and water management issues. With continued research and improved construction practices, pervious concrete has strong potential for wider adoption in sustainable infrastructure development.

11. REFERENCE

- [1] ACI Committee 522, “Report on Pervious Concrete”, ACI 522R, American Concrete Institute, USA.
- [2] Tennis, P. D., Leming, M. L., and Akers, D. J., “Pervious Concrete Pavements”, Portland Cement Association (PCA), USA.
- [3] Neville, A. M., “Properties of Concrete”, Pearson Education, London.
- [4] Mehta, P. K., and Monteiro, P. J. M., “Concrete: Microstructure, Properties, and Materials”, McGraw-Hill Education.
- [5] Chandrappa, A. K., and Biligiri, K. P., “Pervious concrete as a sustainable pavement material – A review”, Construction and Building Materials, Elsevier.
- [6] Yang, J., and Jiang, G., “Experimental study on properties of pervious concrete pavement materials”, Cement and Concrete Research. IS: 456 – 2000, “Plain and Reinforced Concrete – Code of Practice”,

Bureau of Indian Standards (for general concrete reference).

- [7] ASTM C1688 / C1688M, "Standard Test Method for Density and Void Content of Freshly Mixed Pervious Concrete", ASTM International.
- [8] ASTM C1701 / C1701M, "Standard Test Method for Infiltration Rate of In-Place Pervious Concrete", ASTM International.